

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 11-043523

(43)Date of publication of application : 16.02.1999

(51)Int.Cl.

C08F293/00

H01B 1/12

(21)Application number : 09-215561

(71)Applicant : SHIN ETSU CHEM CO LTD

(22)Date of filing : 25.07.1997

(72)Inventor : HIRAHARA KAZUHIRO

NAKANISHI NOBORU

UENO MASAYA




ISONO YOSHINOBU

TAKANO ATSUSHI

(54) BLOCK-GRAFT COPOLYMER AND SELF-CROSSLINKING SOLID POLYELECTROLYTE PRODUCED BY USING THE SAME AND PRODUCTION OF THE POLYELECTROLYTE**(57)Abstract:**

PROBLEM TO BE SOLVED: To obtain a block-graft copolymer useful for a self-crosslinking solid polyelectrolyte adapted for electric cells, the polyelectrolyte being inexpensive, apart from swelling and dissolving in each kind of electrolytes, excellent in liquid-retainability and mechanical strength.

SOLUTION: This copolymer is obtained by including (A) a block chain of a polymer having a polymerization degree of ≥ 10 , the chain comprising the repeating unit of formula I (R1 is H, etc.; R3 is an alkyl, etc.; (n) is 1 to 100; and a number average molecular weight of the graft chain of formula II is 45 to 4400) and (B) a block chain of a polymer having a polymerization degree of ≥ 30 , the chain comprising the repeating unit of formula III (R4 and R5 are each H, etc.; (n) is 2 or 3; (l+m) is ≥ 300 ; (l:m) is (95 to 5):(50 to 50); and (l) and (m) are subjected to random or alternate sequence) in the A:B ratio of (1 to 30):(30 to 1). The objective copolymer is ≥ 300 in polymerization degree and useful for filmy polymer batteries, etc.

**LEGAL STATUS**

[Date of request for examination]

24.01.2003

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]